

Series

## PLT 4G

**Type:** solvent**Printing process:** pad printing**Ink type:** two-component**Finish:** glossy**Materials:** Aluminium, Ceramic, Chrome metal, Glass, Lacquered surfaces, Metal (in general), Stainless steel, treated Polyacetal (POM) (duroplast)**Main features:**

To obtain a good adhesion on glass, it's absolutely necessary to clean the material and clean any residues of graphite, silicone, dust, grease or fingerprints.

We recommend a preliminary pre-treatment (flame) before production.

- . Good coverage
- . Glossy finish
- . Excellent printability
- . Excellent solidity to acids, bases, greases, many organic solvents and oils.
- . Excellent mechanical resistance
- . Due the resin that composes the ink, it is suggested for short-term outdoor applications.

The pot life of the ink is valid for a specified period of time, up to 8h/20 °C.

Higher temperatures and humidity will reduce pot life (suggested temperature at 20-25 °C and low moisture content in the workplace).

**Certifications:** CLP/ GHS (EC 1272/ 2008), Conflict minerals free, EN 71-3, Reach (EC 1907/ 2006), RoHS

The EN 71:3 Directive is valid for standard shades of one component inks, two component inks, HD shades and for all not standard shades which do not contain metallic shades, metallic pastes or fluorescent pigments or inks.

In order to clarify any doubt on not standard shades, it is always recommended to provide us a specific request.

**Eco-sustainability** (free of): Alogens, Animal origin ingredients, Azodyes, Formaldehyde, G-B Ester, Latex, Melamine, Persistent organic pollutants, Phthalates (listed in RoHS directive).

Note: shades in the fluorescent color chart contain formaldehyde.

Note: all our inks are formulated with non carcinogenic aromatic naphthas as the benzene content is below than 0.1% by weight. IPA contamination are also possible but always below the limit of 1000 ppm.

**Outdoor resistance (years):** 1

Not suitable for outdoor applications.

The used pigments have a solidity from 6 to 8 DIN.

In case of mixing with the transparent bases 70 TR or TP, or with the white 160 or 60 BN, the light fastness and atmospheric agents decrease.

**Drying process:** 20 minutes at room temperature

PLT 4G series dries physically by evaporation of solvents or through chemical reaction.

Drying times depend on various factors:

- . thickness of printed ink layer (single print, multi-layer print).
- . type and amount of thinners/ retarders used.
- . type of oven

## Series

## PLT 4G

- . drying temperature
- . type of substrate on which the ink is deposited.

Ink dries physically by evaporation of solvents:

- . 10 -15 minutes at room temperature (depending on local conditions)
- . 30 -40 sec at 50 °C in an air circulation oven.

(The test performed in our laboratory was carried out under the following conditions: 8 mt/min, cliché at 36 microns, medium thinner PLA at 15%, air circulation oven).

## Two -component drying by polymerization:

The polymerization (chemical reaction process) of the ink occurs about 15 minutes after the addition of the catalyst.

The polymerization times depend mainly on the temperature.

At a minimum temperature of 20 °C, Series PLT 4G ends its cross-linking process in about 6 -7 days. An important increase of temperature accelerates the cross-linking process.

At a temperature of 140 °C (film obtained with a 36 micron cliché, a dilution with a medium thinner of PLA at 15%, 30minutes inside oven) we obtain a film with a high degree of polymerization and with a maximum of solidity.

## **Mechanical and chemical solidity:**

Acids	excellent
Alcohol	excellent
Aliphatic organic solvents	excellent
Aromatic organic solvents	excellent
Bases	excellent
Brake oil	excellent
Detergents	commonly used in dishwashers
Diesel	excellent
Gasoline	excellent
Greases	excellent
Washings	about 300 cycles in the dishwasher in standard conditions of use, 45 -60 °C with low -alkaline detergents. It is necessary to pretreat the material and the printed ink film must be tempered for 30 min at 140 °C.
Water	good

The laboratory tests were carried out on pretreated material with a completely polymerised film (140 °C per 30 mins), using a pad printing cliché at 36 microns, medium thinner PLA at 15%.

Or at room temperature (20 °C) after 6-7 working days.

## Colours range:

Series

## PLT 4G

---

Please refer to the Glossy, Metallic, Fluorescent, Opaque (HD) and Ink System ink color charts. The system are 12 colour shades for mixing of RAL, PMS and HKS colours.

The metallic shades are available only by mixing the relative pastes with the Transparent Base 70 TR.

Gold paste 75 10 -20%

Gold paste 76 10 -20%

Gold paste 77 10 -20%

Bronze paste 78 10 -20%

Silver paste 79 -050 10 -15%

The metallized pastes composed with the relative transparent base 70 TR, due to their particular composition, can oxidize.

The pot-life of the compounded METALLIC PASTES is about 8 working hours. The other metallic shades are ready to use.

System shades are:

1080 yellow, 1081 magenta, 1082 blue, 1083 black, TP paste (CMYK), necessary for making four-color prints. In the range are also included the following shades:

160 HD Opaque white

165 HD Opaque black

---

### Auxiliaries and additives :

PLA medium thinner	20%	
PLD slow thinner	20%	
PLB fast thinner	20%	
PLHG hardener	5%	
Retarder paste	10%	max
Levelling agent	1,5%	
Universal antifoam agent	0,5	
Antisilicone/s	1,5%	
Matting powder	2%	6% max

---

### Ink removal:

PLDL solvent

---

### STORAGE:

Please keep the cans in a dark place, at temperature of 15-25 °C.

If the recommended temperature is higher than the suggested one or the cans are not completely closed, the shelf life and the qualities are drastically reduced.

---

### CLASSIFICATION:

Before using this ink, consult the relevant safety data sheets available.

The safety data sheets provided comply with the **REACH regulation (EC 1907/ 2006)**.

The hazard classification and related label ling are compliant with the **CLP / GHS regulation (EC 1272/ 2008)**.

Series

## PLT 4G

**NOTE:**

Our technical consultancy activity, carried out orally, in writing or through tests or experiments, takes place on the basis of our best knowledge.

However, the same must be considered as information without any binding value, also as regards any third party industrial property rights.

This does not exempt the customer from performing his own checks on the products supplied by us in order to estimate the suitability or otherwise of the procedures and for the purposes intended.

The application, use and transformation of the products take place outside our control possibilities and therefore fall under the exclusive responsibility of the customer.